

TUBERIA ASTM A-53 Y ASTM 106 GRADO B

TENSILE REQUIREMENTS

	SEAMLESS			CONTINUOUS WELDED
	A53 B	A106 B	A106 C	
Tensile strength, min., psi	60,000	60,000	70,000	45,000
Yield strength, min., psi	35,000	35,000	40,000	25,000