

TUBERIA API 5L SEAMLESS & WELDED

TENSILE REQUIREMENTS

API 5L PSL1

Grade	Yield		Tensile	
	min	max	min	max
B	35,000		60,000	
X42	42,000		60,000	
X52	52,000		66,000	
X56	56,000		71,000	
X60	60,000		75,000	
X65	65,000		77,000	
X70	70,000		82,000	

API 5L PSL2

Grade	Yield		Tensile	
	min	max	min	max
B	35,000	65,000	60,000	110,000
X42	42,000	72,000	60,000	110,000
X52	52,000	77,000	66,000	110,000
X56	56,000	79,000	71,000	110,000
X60	60,000	82,000	75,000	110,000
X65	65,000	87,000	77,000	110,000
X70	70,000	90,000	82,000	110,000